

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
2 June 2005 (02.06.2005)

PCT

(10) International Publication Number
WO 2005/050324 A2

- (51) International Patent Classification⁷: **G03F 7/20** (74) Agent: **DORRESTIJN**, Antoon; DSM Intellectual Property, P.O. Box 9, 6160 MA Geleen (NL).
- (21) International Application Number: **PCT/EP2004/012248** (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 28 October 2004 (28.10.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
- | | | |
|------------|------------------------------|----|
| 03078487.0 | 5 November 2003 (05.11.2003) | EP |
| 04075712.2 | 10 March 2004 (10.03.2004) | EP |
| 60/551,629 | 10 March 2004 (10.03.2004) | US |
| 04075984.7 | 31 March 2004 (31.03.2004) | EP |
| 04077144.6 | 23 July 2004 (23.07.2004) | EP |
- (71) Applicant (for all designated States except US): **DSM IP ASSETS B.V.** [NL/NL]; Het Overloon 1, NL-6411 Te Heerlen (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **JAHROMI**, Shahab [NL/NL]; Foldersdreef 32, NL-6216 TE Maastricht (NL). **WIENKE**, Dietrich [DE/NL]; Beuk-Straat 9, NL-6181 KV Elsloo (NL). **BREMER**, Leonardus, Gerardus, Bernardus [NL/BE]; Clos Robinson 19, B-4600 Vise (BE).
- Published:
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A METHOD AND APPARATUS FOR PRODUCING MICROCHIPS

(57) Abstract: Method for producing microchips by using immersion lithography, wherein the immersion fluid comprises an additive so that the refractive index of the immersion fluid is increased relative to the fluid not comprising the additive. The exposure light in the method has improved resolution, so that microchips having an increased integration density are obtained. The invention also relates to the immersion fluid and an apparatus for immersion lithography, comprising the immersion fluid.

WO 2005/050324 A2

A METHOD AND AN APPARATUS FOR PRODUCING MICROCHIPS

5

The invention relates to a method as well as an apparatus for producing microchips by using immersion lithography.

Since the invention of integrated circuits in 1959, the computing power of microprocessors has been doubled every 18 months and every three
10 years a new generation of microchips has been introduced, every time reducing the size of electronic devices. This phenomenon is known as Moore's law. The performance of the microchip is, to a large degree, governed by the size of the individual circuit elements, such as for example copper and aluminium lines, in the microchip. A microchip in general comprises a complex three-dimensional
15 structure of alternating, patterned layers of conductors, dielectrics, and semiconductor films. As a general rule, the smaller the circuit elements, the faster the microchip and the more operations it can perform per unit of time. This phenomenal rate of increase in the integration density of the microchips has been sustained in large by advances in optical lithography, which has been the method
20 of choice for producing the microchips.

A higher degree of integration of the circuit requires a shorter wavelength of exposure light used in the method of producing microchips by optical lithography. Changing the exposure light to shorter wavelengths has indeed been the method of choice to increase the resolution. However, switching
25 to shorter wavelengths is becoming increasingly a daunting task as new exposure tools and materials such as photo-resists must be designed. This is a difficult task and it often results in implementation issues and delays. Therefore chip manufacturers generally tend to postpone the introduction of a new exposure wavelength as long as possible and attempt to prolong the lifetime of an existing
30 technology using alternative approaches. Already for a period of time immersion lithography is considered to be an effective method to improve the resolution limit of a given exposure wavelength. Here the air between the bottom lens of the apparatus for producing the microchips and the silicon wafer having a layer of photoresist on top, is replaced with an immersion fluid, leading essentially to a
35 decrease in effective wave length, see for example: A. Takanashi et al. US Patent

- 2 -

No. 4480910 (1984). Preferably the fluid has a high transparency at least at the wavelength of the exposure light, does not influence the chemistry of the photoresist on top of the silicon wafer used to produce the microchip and does not degrade the surface of the lens.

5" Immersion lithography is for example possible for the wavelengths 248 nm, 193 nm and 157 nm. Because of its transparency at 193 nm water is the main candidate for immersion fluid at this wavelength. (See for example: J.H. Burnett, S. Kaplan, Proceedings of SPIE, Vol. 5040, P. 1742 (2003). Because of exceptional transparency of fluorinated and siloxane-based
10 compounds at 157 nm, such fluids are being considered for 157 nm immersion lithography.

Aim of the invention is to provide a method for producing microchips by using immersion lithography showing further resolution enhancement.

15 Surprisingly this aim is achieved because the immersion fluid comprises an additive so that the refractive index of the immersion fluid is higher than the refractive index of the fluid not comprising the additive.

Preferably the refractive index of the immersion fluid is at least 1% higher, more preferably at least 2% higher, still more preferably at least 5%
20 higher, even still more preferably at least 10% higher, most preferably at least 20% higher than the fluid not comprising the additive. Of course the increase of the refractive index is i.a. dependant from the type of additive and the concentration of the additive in the fluid.

Examples of immersion fluids are water and various types of
25 alkanes as well as in fluorinated and siloxane based fluids. The alkanes may comprise 6 - 10 carbon atoms. The pH of immersion fluid preferably is below 10, more preferably below 8, and even more preferably between 3-7.

Two types of additives may be added. Additives, which are soluble in the pure fluid, and additives, which are insoluble in the pure fluid and
30 therefore must be dispersed as particles, preferably nano particles. As soluble additives, both organic compounds and liquids, and inorganic compounds, for example salts, may be used. In case of water as fluid, examples of organic compounds include: various types of sugars, alcohols such as for example cinnamyl alcohol and ethylene glycol, 2-picoline, phosphorus or sulphur
35 containing compounds, such as for example salts of polyphosphoric acids,

- 3 -

sodium polyphosphate, sodium hexametaphosphate, cesium hexametaphosphate, cesium polyphosphate ethoxy-(ethoxy-ethyl-phosphinothioylsulfanyl)-acetic acid ethyl ester, 1-fluoro-1-(2-hydroxy-phenoxy)-3-methyl-2,5-dihydro-1H-1λ5-phosphol-1-ol and water

5 soluble functionalised silicon oil. Examples of inorganic compounds include: mercury monosulphide, mercury(I) bromide, marcasite, calcite, sodium chlorate, lead monoxide, pyrite, lead(II) sulfide, copper(II) oxide, lithium fluoride, tin(IV) sulphide, lithium niobate and lead(II) nitrate.

The soluble additives may further comprise compounds having

10 the general formulae:



where R is a hydrocarbon group with preferably 1 - 100 carbon atoms, more

15 preferably 1 - 10 carbon atoms. The R group may be partly or fully fluorinated and may have a branched or a cyclic structure or a combination thereof. The groups

A are acidic groups or corresponding salts of for example phosphonic, phosphinic, sulfonic and carboxylic acids. Preferably n is 1 - 10.

Preferably the immersion fluid comprises between 1 and 70 wt.

20 % of the soluble additive, more preferably between 2 and 50 wt.%, still more preferably between 20 and 45 wt.%

Preferably insoluble additives are used. Preferably as insoluble compounds nano particles are used in immersion fluids for example organic, inorganic or metallic nano particles. The average size of the particles is preferably

25 10 times, more preferable 20 times, still more preferably 30 times and even still more preferably 40 times smaller than the corresponding exposure wavelength, the wave length of the exposure light used in the method according to the invention. In this way the average size of the nano particles may be less than 100 nanometer (nm), preferably less than 50 nm, more preferably less than 30 nm,

30 still more preferably less than 20 nm, most preferably less than 10 nm. This results in a high transparency of the immersion fluid, especially at the wave length of the exposure light. The particles may have a minimum size of 0.1 nm.

For measuring the dimensions of the nano-particles the particles are in a very dilute mixture applied on a surface in a thin layer, so that at a

- 4 -

microscopic (for example FE-SEM (Field Emission Scanning Electron Microscopy) or AFM (atomic force microscopy)) photographic image of the layer, the single nano-particles are observable. Than from 100 nanoparticles, ad random selected, the dimensions are determined and the average value is taken.

- 5 In case of particles having an aspect ratio above 1, like platelets, rods or worm-shaped nano-particles, as the size the distance from one end to the most remote other end is taken.

The volume percentage of the nano particles in the fluid is preferable at least 10%, more preferably at least 20%, still even more preferably at least 30%, even still more preferably at least 40%. Most preferably the volume percentage is at least 50%, as this results in a fluid having a high refractive index, a high transparency and low amount of scattering of the incident light. Preferably the volume percentage is below 80%, more preferably below 70%. Examples of inorganic and metallic nano particles include: Aluminium nitride, Aluminium oxide, 15 Antimony pent oxide, Antimony tin oxide, Brass, Calcium carbonate, Calcium chloride, Calcium oxide, Carbon black, Cerium, Cerium oxide, Cobalt, Cobalt oxide, Copper oxide, Gold, Hastelloy, Hematite- (alpha, beta, amorphous, epsilon, and gamma), Indium tin oxide, Iron-cobalt alloy, Iron-nickel alloy, Iron oxide, Iron oxide, Iron sulphide, Lanthanum, Lead sulphide, Lithium manganese oxide, 20 Lithium titanate, Lithium vanadium oxide, Luminescent, Magnesia, Magnesium, Magnesium oxide, Magnetite, Manganese oxide, Molybdenum, Molybdenum oxide, Montmorillonite clay, Nickel, Niobia, Niobium, Niobium oxide, Silicon carbide, Silicon dioxide preferably amorphous silicon dioxide, Silicon nitride, Silicon nitride, Yttrium oxide, Silicon nitride, Yttrium oxide, Silver, Specialty, 25 Stainless steel, Talc, Tantalum, Tin, Tin oxide, Titania, Titanium, Titanium diboride, Titanium dioxide, Tungsten, Tungsten carbide- cobalt, Tungsten oxide, Vanadium oxide, Ytria, Yttrium, Yttrium oxide, Zinc, Zinc oxide, Zirconium, Zirconium oxide and Zirconium silicate. Best results are obtained by using particles of a material, which material is highly transparent for radiation at the exposure wave length, for example at a wave length of 248, 193 or 157 nm, for 30 example the material having a transmission of at least 50%, as measured over a theoretical light path of 1mm.

In a preferred embodiment nano particles comprising an Al^{3+} -compound are used in the immersion fluid of the process according to the invention. This is because such an immersion fluid has not only a very high 35

refractive index, but is also highly transparent. Good examples of such particles include Al_2O_3 preferably crystalline $\alpha\text{-Al}_2\text{O}_3$ (Sapphire) and $\gamma\text{-Al}_2\text{O}_3$. Further suitable types of Al_2O_3 are mentioned in Z. Chemie. 25 Jahrgang, August 1985, Heft 8, p. 273-280. In this case good results are obtained if the immersion fluid
5 comprises 25 - 65 vol.% of the nano particles comprising the Al^{3+} -compound. Preferably an immersion fluid comprising 25 - 45 vol.%, more preferably 30 - 40 vol.% of the particles is used. Also good results are obtained by using nano particles of fused amorphous SiO_2 , MgO , nanodiamond, MgAl_2O_4 or nano particles comprising a mixture of fused amorphous SiO_2 and Al_2O_3 . Such
10 immersion fluids not only have favourable optical properties, like a high refractive index and a high transparency, but is also well processable in the standard apparatus for producing microchips. For example the viscosity is low enough, so that the immersion fluid can be pumped easily.

It is known to the skilled person how to make nano particles and
15 stable dispersions of the nano particles in immersion fluids.

For the preparation of nano particles both wet and solid state techniques may be used. Wet methods include sol-gel techniques, hydrothermal processing, synthesis in supercritical fluids, precipitation techniques and micro emulsion technology. Solid state techniques include gas phase methods like flame /
20 plasma techniques and mechano-chemical processing. In particular good results are obtained with wet methods such as sol-gel techniques. The sol-gel reaction can be carried out in aqueous media in which case the particles are charged stabilised. The counter ions are chosen in such a way to ensure high optical transmission at corresponding wavelengths. Preferably phosphorous containing counter ions such as
25 phosphoric acid are used. Alternatively the sol-gel reaction may be carried out in non-aqueous media for example alkanes like decane or cyclic alkanes like decaline. In this case, the nano-particles are stabilised by addition of suitable dispersing agents. In this way high concentration, so high refractive index, and low viscosity are obtained. To ensure low absorption at deep-UV wavelengths, preferably fluorinated dispersing
30 agents are used. After the sol-gel synthesis at ambient pressures, the fluid containing nanoparticles may be heated under pressure to increase the density and also change the crystalline structure of particles. In this way, particles with superior optical properties such as high refractive index can be produced.

Also a combination of the flame hydrolysis and a wet method may
35 be used in which the particles, produced at elevated temperatures, are directly

deposited in the fluids such as water or alkanes such as for example decane or cyclic alkanes such as for example decaline. This method has the advantage that aggregation and agglomeration of highly pure nano-particles is prevented.

It is also possible to use an immersion fluid in the process according to the invention, comprising a mixture of one or more soluble and one or more insoluble additives.

In a further preferred embodiment a fluid is used comprising transparent particles having a refractive index higher than the refractive index of the pure fluid and the additive in an amount, such that the refractive index of the fluid comprising the additive is equal to the refractive index of the transparent particles. Normally because of their size the transparent particles would scatter at least part of the exposure light. However, in this way because the refractive index of the transparent particles is equal to the refractive index of the surrounding fluid, the particles will not scatter any of the exposure light.

The transparent particles for example have an average size of larger than 0.4 microns, preferably of 0.5 - 1000 microns. More preferably the transparent particles have an average size of 1 - 100 microns. Even more preferably 90 wt. % of the transparent particles have a size between 1 and 10 microns, most preferably between 4 and 10 microns.

Preferably the particles have a broad weight distribution and a spherical shape. In this way a high loading of the fluid with the transparent particles is possible, while the fluid still can be handled very well in the process for producing the chips, the fluid still having a very high transparency.

The weight percentage of transparent particles in the immersion fluid containing the additive in an amount, such that the refractive index of the fluid comprising the additive is equal to the refractive index of the transparent particles, is preferably higher than 20%, more preferably higher than 40%, and even more preferably higher than 60%.

The transparent particles may consist of a material having a transmission of least 40% (as measured over a theoretical light path of 1mm). Preferably this transmission is at least 60%, more preferably at least 80%, still more preferably at least 90 %, most preferably at least 95%. Examples of suitable transparent particles are particles of transparent crystals, for example SiO₂, Al₂O₃, MgO and HfO₂. Preferably amorphous SiO₂ particles, sapphire particles or MgO particles are used.

More preferably particles of fused amorphous SiO_2 are used, having a purity of at least 99 wt.%, more preferably at least 99.5 wt.%, still more preferably at least 99.9 wt.%. In this way a fluid having still further improved transparency is obtained

5 Examples of particles of fused amorphous SiO_2 suitable for use in the immersion fluid are of the Lithosil™ series preferably Lithosil™Q0/1-E193 and Lithosil™Q0/1-E248 (produced by Schott Lithotec), and fused amorphous SiO_2 of the HPFS series with the Corning code 7980 (produced by Corning) as used for the production of lenses for apparatus for the production of chips. Such
10- fused amorphous SiO_2 is very pure and therefore may have a transparency of more than 99%. A method of producing such particles is by flame hydrolysis, a method known to the person skilled in the art.

In order to increase the refractive index of the particles of fused amorphous SiO_2 it is possible to dope the particles with small amounts of suitable
15 doping elements, for example Germanium.

In the fluid comprising the transparent particles, as the additive one or more of the above-referred soluble or insoluble additives may be used. Preferably an additive that is soluble in the fluid is used, preferably cesium sulphate, cesium hexametaphosphate or sodium hexametaphosphate.

20 In a further preferred embodiment a fluid is used comprising transparent particles which are functionalised on their surface in such a manner that they become dispersible in the immersion fluid. This is for example possible by grafting the particles with a surfactant, preferably a polymeric surfactant. It is also possible for purpose of dispersing the transparent particles to add a
25 surfactant to the immersion fluid comprising the transparent particles.

In a preferred embodiment the method according to the invention comprises the steps of:

- a) measuring the refractive index of the immersion fluid directly or indirectly,
- b) adjusting the refractive index of the immersion fluid at a predetermined value
30 by adding extra, pure fluid or adding extra additive to the immersion fluid.

In this way fluctuations in the refractive index due to variations in temperature and concentration of the additive are compensated for.

The refractive index may be measured as such directly. It is also possible to measure one or more other parameters, being a measure for the

- 8 -

refractive index. In case the immersion fluid comprises the transparent particles and the additive in an amount, such that the refractive index of the fluid comprising the additive is equal to the refractive index of the transparent particles, it is possible to determine the light scattering of the transparent particles and to add pure fluid or additive to reduce the light scattering. The addition of extra pure fluid may suitably be carried out by mixing extra pure fluid with the immersion fluid. The addition of extra additive may suitably be carried out by mixing a concentrated solution or dispersion of the additive in the pure fluid with the immersion fluid.

10. A still further preferred embodiment of the method according to the invention comprises the steps of
- a) transporting the immersion fluid after being used in the production of a microchip to a cleaning unit,
 - b) cleaning the immersion fluid
 - 15 c) recycling the cleaned immersion fluid into the process for producing the chips.

Due to the extraction of components from the photoresist layer on top of the wafer, possible chemical changes in the fluid components during the exposure step and further reasons, the immersion fluid will tend to be contaminated. This means that after a certain period of using the fluid in the process of the present invention, the fluid has to be refreshed. However this increases fluid consumption and negatively influences the process economics. Surprisingly it is possible to clean the fluid and recycle the cleaned fluid into the process of the present invention.

Cleaning of the fluid is suitably carried out by cross flow filtration or dead end flow filtration using for example membranes for microfiltration, ultrafiltration, nanofiltration or reverse osmoses. Good results are obtained if a stirred pressure cell is used. An example of a stirred pressure cell is given in Fig. 1.

In Fig. 1 a stirred pressure cell is shown comprising a cell housing 1, having a stirrer 2, and an inlet for the used immersion fluid. Between the cell housing 1 and chamber 5 a membrane 3 is mounted. From gas cylinder 7, via pressured regulator 6 a pressure is applied on top of the fluid in cell housing 1. Due to this pressure fluid comprising contaminants is transported through the membrane in chamber 5 and transported further. In cell housing 1 a concentrated fluid composition comprising particles for example nano particles and/or

transparent particles remains. Thereafter the refractive index of the concentrated fluid is adjusted to its original value again by adding pure fluid and if appropriate soluble additive.

Preferably the immersion fluid has a transmission at one or
5 more wavelength out of the group of 248, 193 and 157 nm of at least 10% through a path-length of 1mm, more preferably at least 20%, still more preferably at least 30%, even still more preferably at least 40%, most preferably at least 50%.

The invention also relates to an apparatus for immersion
lithography for the production of microchips, comprising the immersion fluid.
10

Examples I - 10

Dispersions of nano particles of α -Al₂O₃, γ -Al₂O₃, MgO, MgAl₂O₄
are produced by the sol-gel method. Using this method the corresponding
precursors are first dissolved in water or in decaline and a hydrolysis reaction is
15 initiated. After that a hydro-thermal treatment is carried out followed by a
peptisation step. Immersion fluids are finally produced by diluting the so obtained
dispersions with water, respectively decalin.

Nanoparticles of diamond are first produced by solid-state
method and then dispersed in water and decaline to obtain the immersion fluids.
20 The refractive indices are measured at 193 nm and 248 nm using ellipsometer
VUV-VASE produced by J.A. Woollam Co., Inc (US). The results are shown in
table 1 for different volume percentages of nano particles.

Table 1. Refractive indices (RI) of dispersions of various nanoparticles measured at 193 nm and 248 nm.

Additive	Volume(%)	Average particle size (nm)	RI @ 193 nm in water (decane)	RI @ 248 nm in water (decaline)
α -Al ₂ O ₃	10	5	1.49 (1.58)	-
α -Al ₂ O ₃	40	5	1.63 (1.70)	-
Y-Al ₂ O ₃	10	6	1.48 (1.58)	-
Y-Al ₂ O ₃	40	6	1.62 (1.70)	-
MgO	10	7	1.50 (1.59)	-
MgO	40	7	1.66 (1.72)	-
MgAl ₂ O ₄	10	5	1.48 (1.57)	-
MgAl ₂ O ₄	40	5	1.58 (1.64)	-
Nano-diamond	10	8	-	1.46 (1.52)
Nano-diamond	40	8	-	1.64 (1.70)

In all cases an increase in the refractive index are obtained. Nano diamond particles especially show good results at a wave length of 248 nm.

Example 11-14

Solution of different water soluble additives are prepared. The refractive indices are measured at 193 nm and 248 nm using ellipsometer VUV-VASE produced by J.A. Woollam Co., Inc (US). The data are shown in table 2.

Table 2. Refractive indices (RI) of solutions of various additives measured at 193 nm and 248 nm.

Additive	Wt (%)	RI @ 193 nm in water	RI @ 248 nm in water
Cs_2SO_4	40	1.48	1.42
H_3PO_4	20	1.45	1.40
H_3PO_4	40	1.48	1.42
H_3PO_4	85	1.54	1.49

5 The immersion fluids are used in an apparatus for producing
microchips, based on immersion technology at wave length of 193 nm.

10

CLAIMS

1. Method for producing microchips by using immersion lithography, characterised in that the immersion fluid comprises an additive so that the refractive index of the immersion fluid is higher than the refractive index of the fluid not comprising the additive.
2. Method for producing microchips according to claim 1, characterised in that the refractive index of the immersion fluid is at least 1% higher.
3. Method according to claim 1 or 2, characterised in that the additive is soluble in the immersion fluid.
4. Method according to claim 3, characterized in that the immersion fluid comprises 1 - 70 wt.% of the soluble additive.
5. Method according to claim 1 or 2, characterised in that the additive is insoluble in the immersion fluid.
6. Method according to claim 5, characterised in that the immersion fluid comprises as the insoluble additive nano particles.
7. Method according to claim 6, characterised that the nano particles have an average size that is 10 times smaller than the wavelength of the exposure light.
8. Method according to claim 6, characterised that the nano particles have an average size of less than 100 nm.
9. Method according to any of claims 6-8, characterised in that the fluid comprises at least 10 volume % of the nano particles.
10. Method according to any of claims 6-9, characterised in that the particles are used of a material that has a transmission of at least 50%, as measured over a theoretical light path of 1 mm.
11. Method according to claim 10, characterised in that nano particles comprising an Al³⁺-compound are used.
12. Method according to claim 10, characterised that nano particles of fused amorphous SiO₂, MgO, nanodiamond, MgAl₂O₄ or nano particles comprising a mixture of fused amorphous SiO₂ and Al₂O₃ are used.
13. Method according to any one of claims 1-6, characterized in that the fluid comprises transparent particles having a refractive index higher than the refractive index of the pure fluid and the additive in an amount, such that

- 13 -

the refractive index of the fluid comprising the additive is equal to the refractive index of the transparent particles.

14. Method according to claim 13, characterised in that the transparent particles have an average size of 1 1000 microns.
- 5 15. Method according to any of claims 13 and 14, characterised in that the transparent particles are of transparent crystals of SiO_2 , Al_2O_3 , MgO or HfO_2 .
16. Method according to any of claims 1 -15, characterised in that the method comprises the steps of
 - 10 a) transporting the immersion fluid after being used in the production of a microchip to a cleaning unit,
 - b) cleaning the immersion fluid
 - c) recycling the cleaned immersion fluid into the process for producing the chips.
- 15 17. Apparatus for producing microchips, based on the technology of immersion lithography, characterised in that the apparatus comprises the immersion fluid as used in the process of any one of claims 1-15.

- 1/1 -




Fig. 1

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
2 June 2005 (02.06.2005)

PCT

(10) International Publication Number
WO 2005/050324 A3

(51) International Patent Classification⁷: **G03F 7/20**,
H01L 21/47

(21) International Application Number:
PCT/EP2004/012248

(22) International Filing Date: 28 October 2004 (28.10.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03078487.0 5 November 2003 (05.11.2003) EP
04075712.2 10 March 2004 (10.03.2004) EP
60/551,629 10 March 2004 (10.03.2004) US
04075984.7 31 March 2004 (31.03.2004) EP
04077144.6 23 July 2004 (23.07.2004) EP

(71) Applicant (for all designated States except US): **DSM
IP ASSETS B.V.** [NL/NL]; Het Overloon 1, NL-6411 Te
Heerlen (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **JAHROMI, Shahab**
[NL/NL]; Foldersdreef 32, NL-6216 TE Maastricht (NL).
WIENKE, Dietrich [DE/NL]; Beuk-Straat 9, NL-6181
KV Elsloo (NL). **BREMER, Leonardus, Gerardus,**
Bernardus [NL/BE]; Clos Robinson 19, B-4600 Visé
(BE).

(74) Agent: **DORRESTIJN, Antoon**; DSM Intellectual Prop-
erty, P.O. Box 9, 6160 MA Geleen (NL).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(88) Date of publication of the international search report:
22 September 2005

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: A METHOD AND APPARATUS FOR PRODUCING MICROCHIPS

(57) Abstract: Method for producing microchips by using immersion lithography, wherein the immersion fluid comprises an addi-
tive so that the refractive index of the immersion fluid is increased relative to the fluid not comprising the additive. The exposure
light in the method has improved resolution, so that microchips having an increased integration density are obtained. The invention
also relates to the immersion fluid and an apparatus for immersion lithography, comprising the immersion fluid.

WO 2005/050324 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP2004/012248

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 G03F7/20 H01L21/47

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 G03F H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 03, 31 March 1999 (1999-03-31) & JP 10 340846 A (NIKON CORP.), 22 December 1998 (1998-12-22) abstract & JP 10 340846 A (NIKON CORP.) 22 December 1998 (1998-12-22)	1-17
X	paragraphs '0026! - '0032!; figures 1-3	1-17
X	US 5 900 354 A (BATCHELDER ET AL) 4 May 1999 (1999-05-04) column 6, line 50 - column 7, line 16; figure 3; table 1	1-17
	----- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the International filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the International filing date but later than the priority date claimed

T later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the International search

25 July 2005

Date of mailing of the International search report

01/08/2005

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Thiele, N

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP2004/012248

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 023 231 A (TABARELLI, WERNER W., DR) 4 February 1981 (1981-02-04) page 8, line 10 - page 9, line 19; claims 1,4-10; figures 3,4	1-17
X	ROTHSCHILD M ET AL: "Fluorine-an enabler in advanced photolithography" JOURNAL OF FLUORINE CHEMISTRY, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 122, no. 1, 1 July 2003 (2003-07-01), pages 3-10, XP004437021 ISSN: 0022-1139	1,2,17
A	Chapter 7	3-16
X	US 2001/043404 A1 (HATANO HITOSHI) 22 November 2001 (2001-11-22)	1,2,17
Y	paragraphs '0002!', '0012!', '0013!', '0038!', '0040!	3-16
A	US 6 236 493 B1 (SCHMIDT HELMUT ET AL) 22 May 2001 (2001-05-22) abstract	1-17
A	EP 0 967 513 A (DELEGATION GENERALE POUR L'ARMEMENT) 29 December 1999 (1999-12-29) paragraphs '0011!', '0029!', '0031!; claim 1	1-17
A	US 5 618 872 A (POHL ET AL) 8 April 1997 (1997-04-08) abstract	1-17
A	GB 627 719 A (EASTMAN KODAK COMPANY; GALE FRANCIS NADEAU; EDWIN ERNEST JELLEY) 15 August 1949 (1949-08-15) page 1, column 2, lines 50-66	1-17
E	WO 2005/006026 A (NIKON RESEARCH CORPORATION) 20 January 2005 (2005-01-20) paragraph '0027!	16
E	EP 1 522 894 A (MATSUSHITA ELECTRIC INDUSTRIAL CO., LTD.) 13 April 2005 (2005-04-13) claims 1-10,16; figure 2	16
E	WO 2005/024325 A (TOKYO ELECTRON LTD.) 17 March 2005 (2005-03-17) claim 25	16
A	WO 00/06495 A (MINNESOTA MINING AND MANUFACTURING COMPANY; ARNEY, DAVID, S; WOOD, THO) 10 February 2000 (2000-02-10)	1,2,17
Y	page 1, lines 8-20; claims 1,14; examples 1-10	3-16

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/012248

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 10340846	A	22-12-1998	NONE	
US 5900354	A	04-05-1999	WO 9901797 A1	14-01-1999
EP 0023231	A	04-02-1981	EP 0023231 A1	04-02-1981
			AT 1462 T	15-08-1982
			DE 2963537 D1	07-10-1982
US 2001043404	A1	22-11-2001	JP 2001272604 A	05-10-2001
US 6236493	B1	22-05-2001	DE 19613645 A1	09-10-1997
			AT 204991 T	15-09-2001
			CN 1214773 A ,C	21-04-1999
			DE 59704453 D1	04-10-2001
			WO 9738333 A1	16-10-1997
			EP 0891565 A1	20-01-1999
			ES 2160343 T3	01-11-2001
			JP 2000508783 T	11-07-2000
EP 0967513	A	29-12-1999	FR 2780514 A1	31-12-1999
			EP 0967513 A1	29-12-1999
US 5618872	A	08-04-1997	DE 4219287 A1	16-12-1993
			AT 186061 T	15-11-1999
			DE 59309852 D1	02-12-1999
			WO 9325611 A1	23-12-1993
			EP 0644914 A1	29-03-1995
			JP 7507823 T	31-08-1995
			KR 263796 B1	16-08-2000
GB 627719	A	15-08-1949	NONE	
WO 2005006026	A	20-01-2005	WO 2005006026 A2	20-01-2005
EP 1522894	A	13-04-2005	JP 2005136374 A	26-05-2005
			EP 1522894 A2	13-04-2005
			US 2005074704 A1	07-04-2005
WO 2005024325	A	17-03-2005	US 2005046934 A1	03-03-2005
			WO 2005024325 A2	17-03-2005
WO 0006495	A	10-02-2000	WO 0006495 A1	10-02-2000
			AU 744976 B2	07-03-2002
			AU 2018699 A	21-02-2000
			AU 8761498 A	21-02-2000
			CA 2338917 A1	10-02-2000
			CA 2338920 A1	10-02-2000
			DE 69827166 D1	25-11-2004
			EP 1112228 A1	04-07-2001
			EP 1105430 A1	13-06-2001
			JP 2002521305 T	16-07-2002
			JP 2003521556 T	15-07-2003
			WO 0006622 A1	10-02-2000
			US 6329058 B1	11-12-2001